

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions and listings of claims in the Application. No new matter has been introduced by way of the claim amendments. Current additions to the claims are noted with underlined text. Current deletions from the claims are indicated by text ~~striketrough~~ or [[double bracketing]]. The status of each claim is indicated in parenthetical expression following the claim number.

WHAT IS CLAIMED IS:

1 – 35. (Cancelled)

36. (Previously Amended) A product made by the process comprising:

- (a) selecting a plurality of carbon nanotubes; and
- (b) reacting the plurality of carbon nanotubes with an aryl diazonium specie to form carbon nanotubes derivatized with an aryl moiety, wherein reacting comprises bonding said aryl moiety to the carbon nanotube surface carbon atoms, wherein there is at least about one aryl moiety to forty carbon atoms on the carbon nanotube surface.

37. (Previously Presented) The product of claim 36 further comprising dispersing the derivatized carbon nanotubes in a solvent.

38. (Previously Amended) A product made by the process comprising:

- (a) selecting an assembly of single-wall carbon nanotubes;
- (b) immersing the assembly in a solution comprising an aryl diazonium specie; and
- (c) applying a potential to the assembly to electrochemically react the assembly with the aryl diazonium specie, wherein electrochemically reacting comprises bonding an aryl moiety to the carbon nanotube surface carbon atoms, wherein there is at least about one aryl moiety to forty carbon atoms on the carbon nanotube surface.

39. (Previously Amended) The product of claim 36 further comprising pre-forming the aryl diazonium specie.
40. (Previously Amended) The product of claim 36 further comprising:
 - (c) mixing a precursor of the aryl diazonium specie with the plurality of carbon nanotubes; and
 - (d) generating the aryl diazonium specie, wherein the plurality of carbon nanotubes comprise a plurality of single-wall carbon nanotubes.
41. (Previously Presented) The product of claim 36, wherein the plurality of carbon nanotubes comprise single-wall carbon nanotubes.
42. (Previously Presented) The product of claim 41, wherein the single-wall carbon nanotubes have an average diameter of at most about 0.7 nm.
43. (Previously Amended) The product of claim 36, wherein the plurality of carbon nanotubes are electrochemically reacted with the aryl diazonium specie.
44. (Previously Amended) The product of claim 36, wherein the plurality of carbon nanotubes are thermally reacted with the aryl diazonium specie.
45. (Previously Amended) The product of claim 36, wherein the aryl diazonium specie is generated *in situ*.
46. (Previously Amended) The product of claim 36, wherein the aryl diazonium specie is preformed before the plurality of carbon nanotubes are thermally reacted with the aryl diazonium specie.
47. (Previously Amended) The product of claim 36, wherein the plurality of carbon nanotubes are photochemically reacted with the aryl diazonium specie.
- 48 – 49. Cancelled.

50. (Previously Amended) The product of claim 36, wherein the plurality of carbon nanotubes is an assembly of carbon nanotubes.
51. (Previously Amended) The product of claim 50, wherein the assembly is selected from the group consisting of a bucky paper and a mat.
52. (Previously Amended) The product of claim 50 further made by the process comprising:
 - (a) immersing the assembly in a solution comprising the aryl diazonium specie; and
 - (b) applying a potential to the assembly.
53. (Previously Presented) The product of claim 52, wherein the potential is a negative potential.
54. (Previously Presented) The product of claim 52, wherein the solution further comprises a supporting electrolyte specie.
55. (Previously Presented) The product of claim 52, wherein the step of applying a potential to the assembly comprises holding the assembly with an alligator clip treated with a colloidal silver paste.
- 56 – 57. Cancelled.
58. (Previously Presented) The product of claim 36, further made by the process comprising sonicating the derivatized carbon nanotubes.
59. (Cancelled).
60. (Previously Amended) The product of claim 36 or 38, wherein there is at least about one aryl moiety to thirty carbon atoms on the carbon nanotube surface.
61. (Previously Presented) The product of claim 36, wherein the reaction is a thermal reaction at a temperature of at most about 200° C.

62. (Previously Presented) The product of claim 36, wherein the reaction is a thermal reaction at a temperature of at most about 60° C.
63. (Cancelled)
64. (Previously Amended) The product of claim 36 further comprising photochemically treating the mixture of the plurality of carbon nanotubes and the aryl diazonium specie.
65. (Previously Presented) The product of claim 64, wherein the photochemical treatment comprises the use of an ultraviolet light source.
66. (Previously Presented) The product of claim 64, wherein the photochemical treatment comprises the use of a visible light source.
67. (Previously Amended) The product of claim 40, wherein the precursor of the aryl diazonium specie is an aniline derivative and the aryl diazonium specie is generated with a nitrite.
68. (Previously Amended) A solution of single-wall carbon nanotubes made by the process comprising:
- (a) providing a plurality of derivatized single-wall carbon nanotubes, wherein:
 - (i) an aryl diazonium specie derivatized the plurality of single-wall carbon nanotubes with an aryl moiety bonded to the carbon nanotube surface carbon atoms; and
 - (ii) there is at least about one aryl moiety to forty carbon atoms on the carbon nanotube surface; and
 - (b) mixing the plurality of derivatized single-wall carbon nanotubes in a solvent, wherein the derivatized plurality of carbon nanotubes are dispersed in the solvent.
- 69 – 87. (Cancelled)
88. (Previously Amended) A product made by the process comprising:
- (a) preparing an assembly, wherein

- (i) the assembly comprises a first plurality of carbon nanotubes and a second plurality of carbon nanotubes; and
 - (ii) wherein the carbon nanotubes in the first plurality and the carbon nanotubes in the second plurality can be individually addressed electronically;
 - (b) immersing the assembly in an aryl diazonium specie;
 - (c) applying a negative potential to the assembly to cause the first plurality to essentially come in contact with the second plurality; and
 - (d) electrochemically reacting the assembly with the aryl diazonium specie, wherein electrochemically reacting comprises bonding an aryl moiety to the surface of the carbon nanotubes comprising the assembly at the cross points of the first plurality and the second plurality.
89. (Previously Amended) A product made by the process comprising:
- (a) preparing an assembly of carbon nanotubes, wherein
 - (i) the assembly comprises a first plurality of carbon nanotubes and a second plurality of carbon nanotubes; and
 - (ii) wherein the carbon nanotubes in the first plurality and the carbon nanotubes in the second plurality can be individually addressed electronically;
 - (b) immersing the assembly in a first aryl diazonium specie;
 - (c) applying a potential to the assembly in a first direction to cause the first plurality to essentially come in contact with the second plurality;
 - (d) electrochemically reacting the assembly with the first aryl diazonium specie, wherein electrochemically reacting comprises bonding a first aryl moiety to the surface of the carbon nanotubes comprising the assembly at the cross points of the first plurality and the second plurality;
 - (e) immersing the assembly in a second aryl diazonium specie;
 - (f) applying a potential to the assembly in a second direction to cause the second plurality to essentially come in contact with the first plurality; and
 - (g) electrochemically reacting the assembly with the second aryl diazonium specie, wherein electrochemically reacting comprises bonding a second aryl moiety to the surface

of the carbon nanotubes comprising the assembly at the cross points of the first plurality and the second plurality.

90. (Previously Presented) The product of claim 88, wherein the carbon nanotubes of the first plurality comprise single-wall carbon nanotubes and the carbon nanotubes of the second plurality comprise single-wall carbon nanotubes.
91. (Previously Presented) The product of claim 88, wherein the assembly is a crossbar architecture of carbon nanotubes.
92. (Previously Presented) The product of claim 88, wherein the preparation of the assembly comprises fluid flow over a patterned surface.
93. (Previously Presented) The product of claim 88, wherein the preparation of the assembly comprises direct carbon nanotube growth between posts.
- 94 – 130. (Cancelled)
131. (Previously Amended) The product of claim 36, 38 or 68, wherein the product is further comprised by about 1 in 20 to about 1 in 40 of the carbon nanotube surface carbon atoms derivatized with an aryl moiety.
- 132 – 139. (Cancelled)